

## POLYWALL™ & NRP® WALL PANELS

#### **POLYWALL/MATTE TEXTURE**

Thickness: .060" Bright White, Almond

4' x 8', 10'

### NRP/CRACKED-ICE TEXTURE

Thickness: .090" Bright White, Almond

4' x 8', 10'





#### **FEATURES:**

- 100% waterproof
- Fiberglass-free
- · Does not support mold, mildew, or bacteria growth
- Chemically inert
- Color goes all the way through
- Made from 100% recycled resins
- USDA compliant, CFIA approved

#### **BENEFITS:**

- Non-absorbent: no swelling, rotting or water discoloration
- · No irritating, harmful fiberglass dust
- Hygienic: does not contribute to "sick building syndrome"
- Not affected by acids, harsh chemical solvents or petroleum products
- For interior use
- Scratches don't show
- Extended product life
- · Passes most interior building codes
- Suitable for use in federally inspected food processing plants

# **PLAS-TEX® THICK PANELS**

### **THICK PANELS**


Thicknesses: 1/4" - 5/8" Bright White Matte

1/4" x 4' x 8', 10' 3/8" x 4' x 8', 10' 1/2" x 4' x 8', 10' 5/8" x 4' x 8'

1/4" White & Black in stock, other thicknesses and colors available MOQ.

Thick Panels are not Fire Rated







PROPERTY	TEST METHOD	RESULT
Smoke developed	ASTM E84	<450
Flame spread	ASTM E84	<75
Cleanability	NEMA LD 2005 3.4	No Effect
Stain resistance	NEMA LD 2005 3.4	12
Coefficient of lineal thermal expansion	ASTM D-696	3.84 X 10 <sup>-₅</sup> in/in/deg F
Mold/mildew resistance	ASTM D-3273	10
Gardner impact	ASTM D-5420	22.6 in/lb @ 23.1 deg C
Gardner impact	ASTM D-5420	5.9in/lb at -20 deg C
Volatile Organic Compounds	EPA-8260	All below detectible limits
	ı	



